

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C09J 11/00, 201/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/33860 (43) International Publication Date: 6 August 1998 (06.08.98)</p>
<p>(21) International Application Number: PCT/US98/02109 (22) International Filing Date: 5 February 1998 (05.02.98) (30) Priority Data: 08/795,617 5 February 1997 (05.02.97) US (71) Applicant: H.B. FULLER LICENSING & FINANCING, INC. [US/US]; 1200 Willow Lake Boulevard, St. Paul, MN 55110-5132 (US). (72) Inventor: FISCHER, Carolyn, A.; 1200 Willow Lake Boule- vard, St. Paul, MN 55110-5132 (US). (74) Agents: FISCHER, Carolyn, A.; 1200 Willow Lake Boulevard, St. Paul, MN 55110-5132 (US) et al.</p>	<p>(81) Designated States: CA, CN, JP, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: HOT MELT ADHESIVE COMPRISING AN ENCAPSULATED INGREDIENT (57) Abstract <p>The present invention is hot melt adhesive composition comprising at least one ingredient present in an encapsulated form. The encapsulated ingredient may be any known hot melt adhesive formulation ingredient as well as any hot melt adhesive additive such as antioxidants and fragrances for which there is a desirable change in adhesive properties by isolating such ingredient for a duration of time. The encapsulated ingredient is released from the shell by means of pressure, temperature, diffusion, pH, light, radiation, ultrasound, and combinations thereof. Hot melt adhesive compositions comprising at least one encapsulated ingredient are useful for a variety of novel products including self-supported friction glue sticks, non-tacky pelletized pressure sensitive adhesives, cohesive adhesive systems, hot melt adhesive compositions exhibiting improved thermal stability and odor, as well as for a variety of other adhesive applications.</p></p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

HOT MELT ADHESIVE COMPRISING AN ENCAPSULATED INGREDIENT

Field of the Invention

The present invention is a hot melt adhesive composition comprising at least one
5 ingredient present in an encapsulated form. The encapsulated ingredient may be any
known hot melt adhesive formulation ingredient as well as any hot melt adhesive
additive such as antioxidants and fragrances for which there is a desirable change in
adhesive properties by isolating such ingredient for a duration of time. The encapsulated
ingredient is released from the shell by means of pressure, temperature, diffusion, pH,
10 light, radiation, ultrasound, and combinations thereof. Hot melt adhesive compositions
comprising at least one encapsulated ingredient are useful for a variety of novel products
including self-supported friction glue sticks, non-tacky pelletized pressure sensitive
adhesives, cohesive adhesive systems, hot melt adhesive compositions exhibiting
improved thermal stability and odor, as well as for a variety of other adhesive
15 applications.

Background of the Invention

The use of microencapsulated ingredients in the manufacture of pharmaceuticals,
pesticides, paints, and water-based adhesives is known. The most widely-known use of
20 microcapsules has been in the product generally known as carbonless paper wherein
microcapsules provide a controlled release of a color forming reagent core which is
released when pressure is applied.

Landis, U.S. Patent No. 5,532,293 discloses an adhesive system for tamper-
evident envelopes. The adhesive system comprises a dried cohesive latex containing
25 gelatin and a plurality of solvent-filled microcapsules. Applying pressure ruptures the
microcapsules causing the solvent to be released, dissolving the cohesive material and
forming a bond. The solvent dissolves the cohesive material without substantially
dissolving the non-adherent material.

Japanese Patent Application No. 6[1994]-172725 discloses a water dispersible
30 resin composition containing 10.0 wt-% to about 90.0 wt-% of encapsulated plasticizer
alone or in combination with a tackiness-rendering agent having non-adhesive shells and

having an average particle diameter of 10-300 pm and 10.0 wt-% to about 90.0 wt-% of a tackifier characterized by increased tackiness after the shells of the encapsulated plasticizer are destroyed with pressure. This patent application teaches the use of conventional water based plasticizers such as phthalic acid esters and phosphoric acid esters in combination with conventional water-based tackifiers such as acrylic-type tackifiers, natural rubber, butyl rubber, styrene-butadiene rubber and other synthetic rubber compounds.

U.S. Patent No. 2,800,458, issued July 23, 1957 teaches oil-containing microscopic capsules and the method of making, for use in aqueous dispersion transfer films.

Although water-based adhesive compositions comprising microencapsulated solvent and plasticizer have been disclosed to some extent as mentioned above, microencapsulated ingredients have never been utilized in a hot melt adhesive composition.

EP 0 531 618 A1 teaches a cohesive composition, which is tack free when cooled to room temperature and will only adhere to itself, including 60 to about 95 parts by weight of an amorphous polyalphaolefin hydrocarbon. This composition is useful as a cold seal composition for packaging, and related applications. Cohesive cold seal compositions are those which exclusively form bonds to themselves at room temperature.

Commercially available water-based glue-sticks typically are supplied in a container for the purpose of protecting the adhesive from prolonged exposure to air, which will solidify the glue-stick surface, as well as to support and contain the adhesive, as such compositions are much too pliable to maintain a stick like shape in the absence of a container.

Hot melt adhesives are used widely for a variety of applications including packaging and bookbinding wherein various wood pulp based substrates are bonded to each other. Hot melt adhesives typically comprise at least one thermoplastic polymer and at least one additional thermoplastic ingredient selected from the group consisting of tackifying resins, plasticizers, waxes, and mixtures thereof. Additionally, for hot melt pressure sensitive adhesives (PSAs) at least one ingredient is normally a liquid at ambient temperature. The liquid ingredient imparts the pressure sensitivity or surface

tackiness at ambient temperature. Hot melt PSAs are most commonly applied to tapes, labels, medical devices and for various uses in disposable products such as disposable diapers and feminine napkins, for product assembly, elastic attachment, and garment attachment applications. Hot melt PSAs are often the preferred adhesive technology due to the ability to bond difficult to bond substrates such as polyolefin films and nonwoven materials at high line speeds without the additional drying step that is needed for water-based and solvent-based adhesives. The introduction of water or other solvents is particularly a problem for absorbent products as it is very difficult (if not impossible) to completely dry the absorbent. Hot melt PSAs also provide hot tack and immediate green strength, allowing for very high manufacturing rates.

Summary of the Invention

The present invention is a hot melt adhesive system comprising at least one thermoplastic polymer and at least one ingredient selected from the group consisting of tackifying resins, plasticizers, waxes, and mixtures thereof, wherein at least one ingredient is present in an encapsulated form. The core ingredient is released by at least one mechanism selected from the group consisting of pressure, temperature, diffusion, pH, light, radiation, ultrasound and combinations thereof. Preferably, for hot melt PSAs, the core ingredient is normally a liquid at ambient temperature and is released by means of pressure and/or temperature.

Another aspect of the invention is a hot melt adhesive composition comprising at least one additive selected from the group consisting of antioxidants, pigments, dyes, fragrances, fire retardants, and mixtures thereof wherein said additive is present in an encapsulated form.

Another aspect of the present invention is to provide an improved hot melt cohesive adhesive system.

Another aspect of the invention is to provide an adhesive glue-stick comprising at least one thermoplastic polymer and at least one normally liquid ingredient selected from the group consisting of liquid polymers, liquid tackifying resins, liquid plasticizers, and mixtures thereof; wherein said normally liquid ingredient is present in an encapsulated form. The glue-stick produces an adhesive deposition upon application of pressure.

Another aspect of the invention is to provide a thermoplastic composition having improved thermal stability comprising at least one antioxidant encapsulated in a shell.

Another aspect of the invention is to provide a thermoplastic composition having improved odor comprising a fragrance encapsulated in a shell.

5 Another aspect of the invention is to provide a clean and efficient means for adding colorants such as dyes and pigment to thermoplastic compositions.

Another aspect of the invention is to provide a hot melt pressure sensitive adhesive pellet or capsule having a non-tacky surface prior to the release of the encapsulated ingredient.

10 Other aspects of the invention will become apparent in the forthcoming description and examples.

The present invention is a hot melt adhesive comprising at least one thermoplastic polymer and at least one ingredient selected from the group consisting of tackifying resins, plasticizers, waxes and mixtures thereof, wherein at least one ingredient is present
15 in an encapsulated form. The encapsulated ingredient may also be a hot melt adhesive additive selected from the group consisting of antioxidants, pigments, dyes, fragrances, fire retardants, and mixtures thereof. The encapsulated ingredient is released by a least one mechanism selected from the group consisting of pressure, temperature, diffusion, pH, light radiation, ultrasound and combinations thereof. Preferably, for hot melt PSAs,
20 the core ingredient is normally a liquid at ambient temperature and is released by means of pressure and/or temperature.

"Hot melt adhesive" in the context of the invention means not only the commonly accepted functional meaning - thermoplastic compositions suitable to be applied molten to a material for the purpose of permanent or temporary bonding, but also those
25 adhesives wherein the ingredients are combined molten, regardless of the end use application temperature. This departure from the more typical definition is necessary to encompass the appropriate breadth of the present invention as will be demonstrated further by the friction activated glue-stick and improved cohesive cold seal adhesive hot melts.

30 Encapsulation is a term applied to the formation from suitable materials of a shell which encloses a core material. The capsules present in the hot melt adhesive system of

the present invention comprise hot melt adhesive ingredient(s) and/or additive(s) as the core material and a shell material that may also be a hot melt adhesive ingredient or alternatively any other ingredient that does not detract from the hot melt adhesive properties both prior to and after rupturing of the shell. This invention relates to capsules having sizes ranging from approximately a micron to a few millimeters, which are generally referred to as microcapsules. This invention also relates to adhesive systems wherein the entire hot melt adhesive composition has been formed into capsules. For this aspect, the capsules are contemplated to be significantly larger, ranging from about 3 mm to about 10 mm. Capsules and/or microcapsules need not be uniformly spherical and may consist of irregularly-shaped objects such as those having a shell surrounding an irregular shaped crystalline core.

Detailed Description of the Invention

The microencapsulated ingredient may be formed by any known microencapsulation technique such as coacervation, interfacial addition and condensation, air suspension, centrifugal extrusion, spray drying, pan coating, and by the M-CAP™ encapsulation process. The preferred microencapsulated method is the M-CAP™ process of forming a dispersion of core material and shell material and applying a pressure shock wave to the dispersion. The M-CAP™ encapsulation process is described in detail in U.S. Patent No. 5,271,881, incorporated herein by reference.

The rate at which a core ingredient is released from the shell is a function of the material properties of the shell material, the thickness of the shell wall, the capsule size, and the composition and thickness of deposition of the hot melt adhesive composition. The microcapsules range in size from about .25 to 250 μm . Preferably, the size ranges from about 5 μm to about 200 μm . More preferable, the size of the microcapsules ranges from about 10 μm to about 200 μm . Furthermore, the shell wall thickness preferably ranges from about 5 to about 95 weight percent of the total microcapsule. For pressure activated and thermally activated shells, preferably the shell wall material is as thin as possible without prematurely releasing the encapsulated ingredient. For hot melt PSA capsules the shell wall thickness may be substantially higher particularly in the

forthcoming embodiment wherein the adhesive composition in its entirety is processed into microcapsules.

The core ingredient may be any known hot melt adhesive formulation ingredient and/or additive for which there is a desirable change in adhesive properties by isolating such ingredient and/or additive for a duration of time. As mentioned previously, hot melt adhesive compositions typically comprise at least one thermoplastic polymer and at least one additional ingredient selected from the group consisting of tackifying resins, plasticizers, waxes, and mixtures, thereof. Typical hot melt adhesive additives include antioxidants, fragrances, colorants such as pigments and dyes, fire retardants, as well as various medicinal components such as antibiotics, antiseptics, antifungal agents, etc. Such additives are often added to enhance or tailor the adhesive properties for specific end uses. Many (but not all) of the ingredients typically used for hot melt adhesives can be found in Rouyer et al., U.S. Patent No. 5,257,491, incorporated herein by reference. The preferred core ingredient depends on the intended end use application for each particular hot melt adhesive.

A variety of shell or wall materials are suitable for microencapsulating the hot melt adhesive ingredient within the core. Table 3, p. 14 of U.S. Patent No. 5,271,881 discloses a list of known natural and synthetic polymers and elastomers which are amenable to microencapsulation processes. The shell or wall material may be complex, having multiple walls of different compositions. Thus, it is possible to have a first capsule having its own core and shell which forms the core for a second capsule having a shell formed from the same or different material. Other polymers than those listed in U.S. Patent No. 5,271,881, particularly block copolymers and polyolefins produced with single-site metallocene catalyst technology such as Dow's Insite™ technology and Exxon's Exact® elastomers are surmised to be preferred shell material polymers, particularly for non-tacky pressure sensitive adhesive pellets and thermally activated shell adhesive applications, as will be described further in the forthcoming examples. The shell material comprises ingredients that do not detract from the adhesive properties.

For pressure activated adhesives, the shell will preferably release the core material at pressures ranging from about .5 psi to about 200 psi, more preferably from about 1 psi to about 70 psi. Polyurea melamine resin is a preferred shell material for

pressure activated hot melt PSAs. For thermally activated shells, preferably the shell material melts at a temperature less than about 400°F, more preferably between about 175°F and 355°F, as the majority of hot melt adhesives currently available have application temperatures in such a range.

5 As previously stated, for pressure activated hot melt PSAs, the microencapsulated ingredient is normally a liquid at ambient temperature. The hot melt adhesive is substantially non-tacky initially prior to release of the flowable core ingredient. Upon application of pressure, the shell material is ruptured, causing release of the microencapsulated core ingredient which in turn mixes with and tackifies the
10 surrounding ingredients. The pressure required to rupture the shells ranges from 1 psi, which can easily be broken by hand, to in excess of about 30 psi, which can be mechanically applied. The tackiness of the adhesive after rupturing of the shell is a function of both the concentration of microcapsules as well and the size of the microcapsules. Preferably, the encapsulated ingredient is present in amounts ranging
15 from about 5 to about 50 percent by weight, more preferably from about 10 to about 40 percent by weight of the total adhesive composition. Higher concentrations of encapsulated ingredients are advantageous for higher viscosity hot melt adhesive applications. The normally liquid ingredient is selected from the group consisting of liquid polymers such as Indopol™ (Amoco) polyisobutylene, liquid tackifiers such as
20 Regalrez™ 1018 (Hercules) and Escorez™ 2520 (Exxon), liquid plasticizers such as paraffinic oils, naphthenic oils, phthalate and benzoate esters and mixtures thereof wherein the softening point is less than about 35°C.

The pressure activated hot melt adhesive significantly departs from traditional hot melt PSAs in that the ingredient imparting pressure sensitivity is temporarily isolated
25 from the other ingredients. Generally, the terminology "hot melt adhesive" has been reserved for applications that are applied and form bonds with other materials while molten. The hot melt PSA of the present invention comprising at least one ingredient present in an encapsulated form may form bonds while molten and/or form bonds after being cooled to ambient temperature. The pressure activated hot melt adhesives of the
30 invention have utility in a variety of applications, particularly for improved cohesive adhesive systems. Cohesive cold seal adhesive systems are those in which the adhesive

is initially applied molten to a substrate such as an envelope or film. Once cooled, the adhesive is essentially non-tacky, yet adheres to itself upon contact. Cohesive cold seal adhesive systems have a variety of applications such as self-sealing envelopes, release paper-free labels and decals, "tabless" diaper tapes, for bonding porous substrates, as well as for adhesive sheets which are commonly used for rapid prototyping (paper molding) and for creating an adhesive sheet bulletin board or adhesive "magnets" which can be affixed to a rigid substrate for the purpose of releasably attaching notes and memos. The cohesive cold seals of the present invention can be formulated to exclusively bond only to themselves or alternatively the resulting adhesives can be formulated to produce sufficient bonds with other substrates and material. This aspect is particularly advantageous for envelope seals which typically employ two adhesive applications which are then bonded to each other. By employing the cohesive cold seal of the present invention, the applicants surmise only a single adhesive application would be needed, as the adhesive would have sufficient bond strength to the envelope material.

Bonding porous substrates is particularly useful for nonwoven applications. In recent years, perforated and apertured polyolefin films have gained acceptance in the marketplace as a topsheet for nonwoven disposable products due to the improved fluid permeability and tactile qualities they provide. It has become increasingly difficult to assemble disposable products on high-speed machinery utilizing these apertured films due to permeation of the pressure sensitive adhesive through the apertures causing tackiness on the body-facing surface. This tackiness is not only an undesirable problem, but can accumulate on the machinery causing considerable down time and loss of productivity. To avoid these problems, the pressure activated hot melt adhesive can be mechanically pressure activated near the end of the assembly process or alternatively after another layer has been introduced which limits the exposure of the activated hot melt PSA to the machinery. Alternatively, the encapsulated ingredient may have a shell which releases the core ingredient upon exposure to ultrasound or radiation. An emitting device can then activate the adhesive near the end of the assembly process or after another layer has been introduced which limits the exposure of the activated PSA.

Hot melt adhesive compositions comprising a normally liquid microencapsulated core ingredient wherein the shells are activated by pressure are also particularly useful

for novel friction-activated glue sticks. Presently, water-based adhesives provided in cartridges or containers are utilized for glue-sticks. The glue-stick of the present invention can be formed in the same manner as typical hot melt glue-sticks wherein after mixing the ingredients with any known hot melt manufacturing technique, the molten adhesive is poured into cylindrical shaped molds. After cooling, the glue-stick is substantially rigid, not needing a support container, and substantially non-tacky to the touch. Upon applying frictional forces to the glue-stick surface, such as rubbing the surface of the glue-stick against a piece of paper, the microencapsulated liquid ingredient is released from the shells, activating the glue-stick, causing deposition of pressure sensitive adhesive to remain on the paper. The composition of the glue-stick ranges from being "removable" to being of sufficient adhesive and cohesive strength to permanently bond paper based substrates. The "removable" friction activated glue-stick is particularly useful for allowing individuals to produce temporary, self-adhering notes by abrasion with paper. A variety of glue-stick shapes are also possible since the hot melt adhesive will retain the shape of the mold it was cast from. This aspect may be particularly attractive for glue-sticks intended for use by children. Crayon sized glue-sticks are envisioned to be most preferred.

Alternatively, the glue stick formed from molten thermoplastic ingredients may be sufficiently pliable and/or tacky such that an auxiliary container would still be desirable to facilitate handling. For this aspect the container may be any of the existing glue stick containers on the market such as plastic glue dispensers, pencil and pen barrels as well as pen cartridges. It may also be desirable to microencapsulate fragrances in the friction activated glue sticks as consumers particularly children, are often attracted to this feature.

Preferable polymers for pressure activated hot melt adhesives include radial, linear and grafted block copolymers such as styrene-isoprene-styrene (SIS), styrene-butadiene-styrene (SBS), and styrene-ethylene/butylene-styrene (SEBS); amorphous polyolefins, particularly linear and substantially linear polyolefins produced with single-site metallocene catalyst technology such as Dow's Insite™ technology and Exxon's Exact® plastomers; ethylene-vinyl acetate (EVA), ethylene-methyl acrylate (EMA), and mixtures thereof. Recycled polyethylene terphthalate (PET) is believed to be particularly

useful for the friction activated glue-sticks when combined with microcapsules of oil, diethyl phthalate, dioctyl phthalate and mixtures thereof. For the supported glue-sticks, combinations of tackifying resin and encapsulated liquid plasticizer in the absence of a thermoplastic polymer are also contemplated.

5 Pressure activated hot melt adhesives preferably further comprise at least one solid tackifying resin. Light colored resins such as Wingtack 95™, a C5 hydrocarbon resin, and Escorez™ 5000 series dicyclopentadiene based resins are particularly preferred for the friction glue-stick.

Up to 20.0% of wax is also useful to increase the rigidity and heat resistance particularly for the glue-stick. Most preferably, the wax concentration ranges from 0 to about 5.0% by weight.

In another aspect it may be desirable to produce water soluble friction activated glue-sticks. For this aspect, water soluble water dispersible thermoplastic ingredients are particularly useful such as polyvinylpyrrolidone-co-vinyl acetate, polyethylene, 15 oxoethylene, polyvinylalcohol, polyethylene oxide as well as others.

In another aspect inorganic salts such as calcium chloride may be added to the glue-sticks to create a heat generating friction glue-stick that is activatable with water. The concentration of inorganic salt ranges from about 5 wt-% to about 30 wt-% to produce the desired result. The inorganic salt may be encapsulated in a water soluble 20 shell such as starch or alternatively may be dispersed in the glue-stick without being encapsulated.

Pressure Activated Hot Melt Adhesive Compositions

	<u>Useful</u>	<u>Preferred</u>	<u>Most Preferred</u>
25 Thermoplastic polymer	5-90 wt-%	10-80 wt-%	10-60 wt-%
Encapsulated Liquid	5-80	10-50	10-40
Solid Tackifying Resin	0-65	10-60	30-60
Wax	0-20	0-10	0-5

30 Thermally activated shells are useful for other purposes, particularly for the addition of colorants such as dyes and pigments, antioxidants, fragrances, etc. These

additives are typically found in hot melt adhesives at concentrations by weight of less than 5.0%, more preferably from about 0.10% to about 2.0%. For this application, a shell material is selected that has a melting point below the application temperature of the hot melt adhesive. During manufacturing, the unencapsulated hot melt adhesive ingredients are initially combined to form a molten mixture. The molten mixture is then cooled below the melt point of the shell material and the encapsulated ingredient added. The encapsulated ingredient is preserved in the hot melt adhesive until the adhesive is melted at a later time by the end user at which point the shell material becomes molten, releasing the encapsulated ingredient. Seeded shells are particularly useful for slow release of an ingredient. For this aspect, only small portions of the shell would become molten, whereas the majority of the shell would remain intact, maintaining the integrity of the microcapsule. The core material then slowly releases from the cavities formed at the melted regions. The rate of release is a function of the number and size of meltable regions which in turn creates the cavities upon melting. Alternatively, the additive is released by means of an increase in pressure.

Hot melt adhesives comprising an additive in a thermally activated shell is particularly advantageous for the addition of volatile components such as fragrances, to insure a specific concentration is present in the final adhesive composition upon reaching the end user. This aspect is also particularly advantageous as a clean and efficient means to add colorants not only to hot melt adhesive compositions but potentially any thermoplastic composition, particularly film grade neat polymers such as poly(ethylene-co-vinyl acetate), polyethylene, and polypropylene.

Another preferred use of thermally activated shells is in PSA capsules or pellets having a non-tacky surface. The hot melt adhesive ingredients which are substantially non-tacky at ambient temperature are first combined with one another using conventional hot melt mixing techniques. The mixture is then cooled to a temperature below the melt point of the shell material of the encapsulated, normally liquid ingredient. The encapsulated, normally liquid ingredient is then added to the mixture and pelletized. Since the normally liquid ingredient is isolated from the other ingredients until melted, the pellets remain non-tacky until melted by the end user. Alternatively, a hot melt adhesive capsule may be formed. In this instance, the polymer or a blend of polymers

and other ingredients form the shell material, whereas the remaining ingredients are blended to form the core material. The core is then encapsulated by any known suitable microencapsulation technique to form hot melt adhesive capsules. For this aspect, the shell material preferably comprises polymer or a mixture comprising polymer tackifying resin, and/or wax. For hot melt pressure sensitive adhesives that can easily be fed through an extruder prior to application, the shell material release mechanism may be pressure rather than temperature. Shell materials activated by pressure are also surmised to be suitable for extruder grades additives such as antioxidants and colorants, as mentioned previously.

10 Diffusion activated shells are those in which the core ingredient may leach through the shell material at ambient conditions. This activation mechanism provides yet another alternative method of adding colorants. For a hot melt PSA, a core material such as a dye can be encapsulated in a shell material, comprising a polymer and/or tackifying resin that would eventually dissolve in the adhesive.

15 Diffusion as well as pH provide appropriate release mechanisms for wetness indicators. For this aspect, a pH or water sensitive shell material would encapsulate a colorant or dye. When such encapsulated colorant is combined with an adhesive, the resulting adhesive composition produces a color change upon being exposed to liquid. This application finds particular utility in the adult incontinence market. Hot melt adhesive compositions for wetness indicators are known from U.S. Patent Nos. 20 5,035,691 and 5,089,548 incorporated herein by reference.

Test Methods

25 Cohesive Adhesives - Self Seal Measurements

Test C1:

Measurement of Minimal Pressure to Self Seal

30 Test samples are prepared by coating the hot melt adhesive molten (350°F) onto 2 mil polyester film using a slot die coater at a coat thickness ranging from about 4 to 10 mils (1 mil = 0.001 inch). Two pieces of coated film are placed in contact with each other

coated side to coated side. The observation is made whether or not the adhesive coatings adhere or not. Adhesion occurs when lifting one sheet causes the other sheet to also be lifted. The two sheets are then manually peeled, and the failure mode, "interfacial" or "cohesive" is noted. "Interfacial" failure refers to adhesive-to-adhesive failure at the adhesive interface wherein the coated films may be separated cleanly into the two original coated films. "Cohesive" failure refers to having a continuous adhesive layer formed upon sealing in which peeling results in destruction of the bond.

Test C2:

10 Finger Pressure

In the event that samples do not seal with minimal pressure (Test C1), the same test is repeated with finger pressure applied over the film. The same observations are recorded as described in Test C1.

15 Test C3:

Adhesion to Polyester with Minimal Pressure

A sample coated onto polyester film, as described in Test C1, is placed in contact with uncoated polyester film. The same observations as described in Test C1 are made.

20 Test C4:

Adhesion to Polyester with Finger Pressure

Test C3 is run under the conditions of Test C2.

Test C5:

25 **Loop tack on Stainless Steel**

Samples coated onto polyester film, as described in Test C1, are cut into 1" by 5" sections and tested with a Chem Instruments LT-100 Loop Tack Tester in accordance with the TLMI Loop Tack Test. The force of delamination is recorded.

30 Test C6:

Surface Tack

Surface tack is measured by touching the surface of the solidified adhesive with a finger. The adhesive is characterized as being "aggressive" meaning a significant level of resistance is experienced when removing one's finger, "removable" meaning a low level of resistance is experienced when removing one's finger, or "tack-free".

Test C7:**Mechanical Self-Seal Properties**

For sheets which do not adhere with finger pressure and result in cohesive failure (Test C2), pressure is applied with a mechanical sealer. The time and pressure is recorded for which a bond is formed which when peeled, produces cohesive failure. Samples were prepared by coating polyester film with a slot die coater as mentioned in Test C1. Two 12" by 1" strips are placed in a Sentinel™ heat sealer. (Contacting both adhesive coated sides of the film.) The jaw pressure and time for which the pressure was applied are noted. Testing was conducted at room temperature (78°C).

Friction-Activated AdhesivesTest A1:

Surface tack is measured by touching the surface of the solidified adhesive by hand. The adhesive is characterized as being "tacky" or "tack-free".

Test A2:

Rigidity is measured by manually flexing a mass of solidified adhesive approximately 1/8" to 1/2" inch thick. The solidified adhesive is evaluated as either "soft"- meaning it is pliable, or "rigid" - meaning it will fracture.

Test A3:

Deposition is measured by rubbing a piece of the solidified adhesive over a piece of white legal notebook paper (UNV 20630 - St. Paul Book & Stationery). The paper is evaluated to determine whether a deposition is present - "yes" or lacking -"no". The

tackiness of the deposition is also characterized as being "permanent" meaning a significant level of resistance is experienced when removing one's finger or "removable" meaning a low level of resistance is experienced.

5 Test A4:

Fiber Tear is measured by first depositing adhesive onto St. Paul Book & Stationery notebook paper according to Test A3, adhering 8" by 2" strips of St. Paul Book & Stationery notebook paper, and removing the strips within 5 minutes. Fiber tear was either observed - "yes" or not observed - "no".

10

Test A5:

Holding Power is measured by adhering strips of paper according to Test A4 and hanging the strips vertically, recording the time the adhesive bond fails ambient temperature.

15

Discussion of Examples

Tables A and C depict adhesive compositions of the present invention comprising an encapsulated ingredient. Materials formulated with encapsulated mineral oil have significantly different tack properties prior to rupturing the shells than after the release of
20 the encapsulated ingredient. Tables B and D depict the test data for the adhesive compositions. Tables A and B are directed toward friction activated glue-stick, whereas Tables C and D are directed toward cohesive cold seal adhesives. Several of the compositions can be found on both tables indicating the versatility of this technology. Accordingly, the presentation of the examples in this manner is not intended to be
25 limiting, as the adhesive compositions themselves are useful for potentially any hot melt adhesive application.

Examples 1 - 18 of Tables A and B depict adhesive compositions directed toward use for glue-sticks having good holding power. Examples 1 - 3, 8 - 9 and 16 - 17 are amendable to adhesive "crayon" applications since the compositions are sufficiently rigid
30 to the extent that a container is not needed and tack-free prior to rupturing the encapsulated oil. Examples 1 - 3 and 16 - 17 exhibit relatively aggressive adhesive

properties in that the adhesive deposition formed upon applying pressure is sufficient to produce fiber tearing bonds with paper like materials. The adhesive composition of Examples 8 - 9 are directed toward temporary bonding since the glue deposition creates a removable, non-destructive bond. Examples 4 - 7 and 10 - 15 are demonstrative of glue-stick compositions preferably provided in a container. The adhesion varies from removable to permanent as in the previous rigid glue-stick examples. Examples 16 and 17 exemplify the use of recycled PET as a base polymer. Examples 19 - 22 represent adhesive compositions of the present invention having the proper balance of adhesion for seal sheet adhesive applications since these examples exhibit minimal adhesion to other substrates and have little to no surface tack in combination with excellent self-adhesion.

Example 19 (5580-6-1) and Comparative Example A (5580-54-3) of Table C are identical in composition with the exception that Comparative Example A comprises a typical hot melt PSA wherein the mineral oil is not encapsulated in a shell whereas in Example 19 the mineral oil is present in an encapsulated form. Comparative Example A has aggressive finger tack and produces 10.4 pounds of loop tack in contrast to Example 19 of the present invention having "0" loop tack and removable finger tack. The pressure required to active or rupture the capsules, resulting in a cohesive layer being formed, depends on the formulation. Several samples, such as Examples 19 - 21 of Tables C and D require little pressure to self-seal, whereas Examples 22 and 24 of Tables C and D require a pressure in excess of that which can be applied by hand.

Comparison of Examples 23 and 24 demonstrate the ability to tailor the properties of the adhesives by varying the shell structure. ESI encapsulated mineral oil differs from 3M's slightly in that the ESI material would not seal in Example 24 (51 - 1), yet Example 23 (6 - 2) demonstrates self-seal properties. The reason is surmised to be the difference in shell wall concentration and hence oil concentration, as shown below.

<u>Material</u>	<u>Capsule Diameter(um)</u>	<u>Core Volume(%)</u>
3M	32	85
ESI	30	76.2

Both materials contain mineral oil encapsulated in a polyurea melamine resin shell. The ESI material is surmised to be more difficult to rupture owing to its greater wall thickness. Heat can also cause activation. Example 26 shows no tack or adhesion to polyester film as prepared and tested under normal conditions. However, upon heating
5 this sample above 200°C, the capsules rupture. Upon cooling, the material has aggressive tack. This shows the utility of capsules to temporarily reduce tack and the ability to generate tack by breaking capsules. This allows for the efficient production of compositions which are initially tack-free yet capable of forming pressure sensitive adhesives upon rupturing of the capsules by means of pressure and/or temperature.

Table A - Friction Activated Glue-stick Adhesive Composition

EX.#	Reference#	Polymer	wt-%	Tackifying Resin	wt-%	Encapsulated	
						Ingredient	wt-%
1	5114-44-1	UE 654-67	13	Zonatac 105L	56.5	(3M) 32 um encap oil	30.5
2	5724-50-1	UE 654-67	13	Zonatac 105L	56.5	(ESI) 30 um encap oil	30.5
3	5724-53-3	UE 654-67	10	Sylvatac 1103	60	(ESI) 30 um encap oil	30
4	5724-54-2	Elvax 205	30	Zonatac 105L	50	(ESI) 30 um encap oil	20
5	5580-6-1	Kraton D1117	20	Zonatac 105L	50	(3M) 32 um encap oil	30
6	5580-61-5	Kraton D1117	20	Escorez 5400	50	(3M) 32 um encap oil	30
7	5724-53-6	Rextac RT 2715	70	none	0	(ESI) 30 um encap oil	30
8	5724-54-3	Elvax 205	20	Escorez 5600	40	(ESI) 30 um encap oil	40
9	5580-6-2	Kraton G1657	20	Zonatac 105L	50	(3M) 32 um encap oil	30
10	5580-6-3	Kraton D1117	20	Escorez 1310LC	50	(3M) 32 um encap oil	30
11*	5580-61-3	Kraton D1117	20	Zonatac 105L	45	(3M) 32 um encap oil	30
12	5724-51-1	Kraton G1657	20	Zonatac 105L	50	(ESI) 30 um encap oil	30
13	5724-51-2	Kraton D1117	20	Escorez 5400	50	(ESI) 30 um encap oil	30
14	5724-54-1	Elvax 205	20	Sylvatac 1103	40	(ESI) 30 um encap oil	40
15	5724-57-3	Kraton D1117	30	Sylvatac 1103	50	(ESI) 30 um encap oil	20
16	5709-7-1	EVCO BC-Bind	80	none		diethyl phthalate	20
17	5709-7-2	EVCO BC-Bind	75	none		diethyl phthalate	25
18	5724-57-1	Engage 8400	15	Escorez 5600	45	(ESI) 30 um encap oil	40

* Example 11 also comprises 5.0% of wax (Okerin 236TP)

Table B - Friction Activated Glue-stick Adhesive Properties

EX.#	Reference#	Test A1 Surface Tack	Test A2 Rigidity	Test A3 Deposition	Test A4 Fiber tear	Test A5 Holding Power
1	5114-44-1	tack-free	rigid	yes, permanent	yes	hold > 1wk
2	5724-50-1	tack-free	rigid	yes, permanent	yes	hold > 1wk
3	5724-53-3	tack-free	rigid	yes, permanent	yes	hold > 1wk
4	5724-54-2	tack-free	soft	yes, permanent	yes	hold > 1wk
5	5580-6-1	tack-free	soft	yes, permanent	yes	hold > 1wk
6	5580-61-5	tack-free	soft	yes, permanent	yes	hold > 1wk
7	5724-53-6	tacky	soft	yes, permanent	yes	hold > 1wk
8	5724-54-3	tack-free	rigid	yes, removable	no	hold > 1wk
9	5580-6-2	tack-free	rigid	yes, permanent	no	hold > 1wk
10	5580-6-3	tack-free	soft	yes, removable	no	hold < 1wk
11	5580-61-3	tack-free	soft	yes, permanent	no	hold > 1wk
12	5724-51-1	tack-free	soft	yes, permanent	no	hold < 1wk
13	5724-51-2	tacky	soft	yes, removable	no	hold < 1wk
14	5724-54-1	tacky	soft	yes, removable	no	hold > 1wk
15	5724-57-3	tacky	soft	yes, removable	no	hold < 1wk
16	5709-7-1	tack-free	rigid	yes, permanent	yes	hold > 1wk
17	5709-7-2	tack-free	rigid	yes, permanent	yes	hold > 1wk
18	5724-57-1	tacky	rigid	yes, removable	no	hold > 1wk

Table C - Cohesion Cold Seal Adhesive Compositions

EX.#	Reference#	Polymer	wt-%	Tackifying Resin	wt-%	Encapsulated	
						Ingredient	wt-%
19	5580-6-1	Kraton D1117	20	Zonatac 105L	50	(3M) 32 um encap oil	30
20	5580-6-3	Kraton D1117	20	Escorez 1310LC	50	(3M) 32 um encap oil	30
21	5580-61-3	Kraton D1117	20	Zonatac 105L	45	(3M) 32 um encap oil	30
22*	5580-61-5	Kraton D1117	20	Escorez 5400	50	(3M) 32 um encap oil	30
23	5580-6-2	Kraton G1657	20	Zonatac 105L	50	(3M) 32 um encap oil	30
24	5724-51-1	Kraton G1657	20	Zonatac 105L	50	(ESI) 30 um encap oil	30
25	5724-51-2	Kraton D1117	20	Escorez 5400	50	(ESI) 30 um encap oil	30
26	5580-21-1	Engage 8400	25	Escorez 1310LC	45	(3M) 32 um encap oil	30
	5580-54-3	Kraton D1117	20	Zonatac 105L	50	Kaydol Mineral Oil	30

* Example 22 also contains 5.0 of wax (Okerin 236TP)

Ingredient List

Description		Supplier
UE 654-67	33% VA/44 MI ethylene-vinyl acetate	Quantum
Elvax 205	28 % VA/800 MI ethylene-vinyl acetate	DuPont
Kraton D-1117	(styrene-isoprene-styrene) block copolymer, 17 wt% styrene, 106 melt index, 40 wt% diblock	Shell
Rextac 2715	amorphous polyalphaolefin	Rexene
Kraton G-1657	(styrene-ethylene-butylene-styrene) block copolymer, 13 wt% styrene, 8 melt index, 35 wt% diblock	Shell
EVCO BC-Binds	polyester (isophthalic acid modified PET)	Evco/Seydel
Engage 8400	30 melt index .870 density metallocene polyolefin	Dow
Zonatac 105	modified terpene	Arizona
Escorez 5400	cyclic aliphatic - hydrogenated	Exxon
Escorez 5600	cyclic aliphatic - hydrogenated	Exxon
Sylvatac 1103	rosin ester	Arizona
Okerin 236 TP	155° F Paraffin Wax	Astor Wax

What Is Claimed:

1. A glue-stick comprising an adhesive composition comprising at least one thermoplastic polymer and at least one normally liquid ingredient selected from the group consisting of liquid tackifying resin, liquid polymers, liquid plasticizers, and mixtures thereof; wherein said normally liquid ingredient is present in an encapsulated form.
2. A hot melt pressure sensitive adhesive composition comprising at least one thermoplastic polymer and at least one normally liquid ingredient selected from the group consisting of liquid tackifying resin, liquid polymers, liquid plasticizers, and mixtures thereof; wherein said normally liquid ingredient is present in an encapsulated form and said adhesive composition is substantially non-tacky prior to release of the encapsulated ingredient.
3. A hot melt adhesive comprising a thermoplastic polymer and at least one ingredient selected from the group consisting of thermoplastic polymers, tackifying resins, plasticizers, waxes and mixtures thereof; wherein at least one ingredient is present in an encapsulated form.
4. A thermoplastic composition comprising at least one encapsulated additive selected from the group consisting of antioxidants, fragrances, pigments, dyes, fire retardants, and mixtures thereof; wherein said additive is present in an encapsulated form.
5. A pressure sensitive adhesive capsule comprising a flowable core material substantially surrounded by a non-tacky shell.
6. The adhesive capsules of Claim 5 wherein the core material is normally a liquid ingredient selected from the group consisting of liquid tackifying resin, liquid polymers, liquid plasticizers, and mixtures thereof.

7. The adhesive composition of Claim 1, wherein said stick produces an adhesive deposition upon application of pressure.
8. The adhesive composition of Claim 1, 2, 3 wherein the normally liquid ingredient of the adhesive composition comprises a plasticizing oil present in an encapsulated form.
9. The adhesive composition of any of Claims wherein the adhesive composition further comprises at least one solid tackifying resin.
10. The glue-stick of Claim 1 wherein said adhesive composition is sufficiently rigid at ambient temperature such that said glue-stick is self-supporting.
11. The hot melt adhesive of any of Claims wherein said encapsulated ingredient is released by at least one mechanism selected from the group consisting of pressure, temperature, diffusion, pH, light radiation, ultrasound and combination thereof.
12. A hot melt pressure sensitive adhesive pellet comprising the composition of Claims 2 and 3.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 98/02109

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C09J11/00 C09J201/00		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) IPC 6 C09J		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Week 9511 Derwent Publications Ltd., London, GB; AN 95-078246 XP002066305 & JP 07 003 239 A (TOYO INK MFG CO) , 6 January 1995 see abstract	2,3,5,6, 9,11,12
X	DATABASE WPI Week 8201 Derwent Publications Ltd., London, GB; AN 82-00873e XP002066306 & JP 56 155 272 A (KANZAKI PAPER MFG CO LTD) , 1 December 1981 see abstract	2,3,5,6, 8,9,11
--- -/--		
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents :		
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed		
"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the international search	Date of mailing of the international search report	
28 May 1998	17/06/1998	
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Mazet, J-F	

1

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 98/02109

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Week 9514 Derwent Publications Ltd., London, GB; AN 95-102071 XP002066307 & JP 07 026 153 A (NITTO DENKO CORP) , 27 January 1995 see abstract ---	5
X	FR 2 340 967 A (BASF AKTIENGESELLSCHAFT) 9 September 1977 see claims ---	4
X	DE 43 01 992 A (TECH-IN GMBH TECHNOLOGIEN FÜR KUNSTSTOFFE UND SONDERWERKSTOFFE) 24 June 1993 see claims -----	4

1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 98/02109

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2340967 A	09-09-1977	DE 2605021 A	18-08-1977
		BE 851317 A	10-08-1977
		GB 1575625 A	24-09-1980
		NL 7700987 A	12-08-1977

DE 4301992 A	24-06-1993	NONE	
